



Panasonic R-1551(W) Prepreg

R-1551(W)

Prepreg

Glass Cloth	Suffix (Article)	Resin Content (%)	Tolerances Resin Content (%)	Gel Time (sec)	Tolerances Gel Time (sec)	min Viscosity (Pasec)	Tolerances Viscosity (Pasec)	Calculated Thickness (mm)
106	PR0106H401	74	+/-2	120	+/-20	40	+/-10	0,056
1078	PR1078H402	63	+/-2	120	+/-20	40	+/-10	0,073
1080	PR1080H401	63	+/-2	120	+/-20	40	+/-10	0,073
1080 HRC	PR1080H402	66	+/-2	120	+/-20	40	+/-10	0,080
2116	PR2116H401	50	+/-2	120	+/-20	40	+/-10	0,110
2116 HRC	PR2116H404	55	+/-2	120	+/-20	40	+/-10	0,125
1504	PR1504H402	46	+/-2	120	+/-20	40	+/-10	0,141
1504 HRC	PR1504H401	50	+/-2	120	+/-20	40	+/-10	0,155
1501	PR1501H401	46	+/-2	120	+/-20	40	+/-10	0,157
7628M	PR7628H401	47	+/-2	120	+/-20	48	+/-10	0,204
7628M HRC	PR7628H403	50	+/-2	120	+/-20	48	+/-10	0,220

7628M = 7628 209g/m²

Other glass cloth types and specifications on request